



Jain (Americas) Inc.

Jain Americas, Inc.

1000 Sheridan St.
Chicopee, MA 01022
888-473-7539

EXCEL CLASSIC PVC FREE FOAM SHEET ASTM REFERENCE SHEET 10-30mm

Excel **Classic** PVC Free Foam Sheet is free from lead, cadmium, barium and other heavy metals.

PROPERTY	TEST	UNIT	VALUE
----------	------	------	-------

PHYSICAL

Density	ASTM D 792	g/cc	0.55
Hardness	ASTM D 2240	Shore 'D'	≥50
Water Absorption	ASTM D570	%	≤ 1.0

MECHANICAL

Tensile Strength	ASTM D 638	Psi	> 2150
Elongation at Break	ASTM D 638	%	>13
E-Modulus	ASTM D 638	Psi	130000-220000
Flexural Strength	ASTM D 790	Psi	>4600
Izod Impact Strength	ASTM D 256	Ft lb/in	≥1.7
Charpy Impact Strength	ASTM D 256	Ft lb/in	≥1.7
Compressive Strength at 10% Deformation	ASTM D 695	%	>900
Screw Hold (typical for 25mm)	ASTM D 1761	Lbs/inch	>400

THERMAL

Vicat softening (B/50)	ASTM D 1525	°F	>160
Coefficient of Linear Thermal Expansion	ASTM D 696	°C ⁻¹	2.483 X 10 ⁻⁵
Thermal Conductivity	ASTM C 177	W/m K	0.05 – 0.07
Heat Deflection Temperature @ 1.8 MPa	ASTM D 648	°F	135
Burning Rate	ASTM D 635	In/min	No burn when flame removed

ELECTRICAL

Surface Resistivity	ASTM D 257	Ω	>1 x 10 ¹⁴
Volume Resistivity	ASTM D 257	Ω-cm	>1 x 10 ¹⁵
Dielectric Constant at 1 MHZ	ASTM D 150	-	1.56
Dielectric Strength	ASTM D 149	KV/cm	

FLAMMABILITY

Country: UK	BS476; Part 7	-	Class 1
Country: USA	UL 94		94 V-0; 94 5-V
Country: France	NFP 92-501		M1

STANDARD DIMENSIONS AND COLOR

Color	White J 1018 & J 1022
Thickness	10 to 30 mm
Width	1000, 1220 & 1560 mm 2050 mm width on request
Length	2000, 2440 & 3050 mm

*Special color, lengths and widths as per customer request

TOLERANCE ON DIMENSIONS

Length	-0, +10 mm
Width	-0, +5 mm
Thickness	+/- (0.1 + 0.05 x S) Where S = thickness of the sheet
Deviation Between Diagonals	mm \geq 6
Warpage on a full sheet	mm \geq 10

ALL INFORMATION GIVEN FOR PROPERTIES ARE BASED ON A TYPICAL SAMPLE, IS ACCURATE TO THE BEST OF OUR KNOWLEDGE, AND IS PROVIDED WITHOUT LIABILITY OR COMMITMENT WHATSOEVER. IN AS MUCH AS JAIN IRRIGATION SYSTEMS LIMITED HAS NO CONTROL OVER THE USE TO WHICH OTHERS PUT ITS MATERIAL, IT DOES NOT GUARANTEE THAT THE SAME RESULTS AS THOSE DESCRIBED HERE, WILL BE OBTAINED. EACH USER OF THE MATERIAL SHOULD MAKE THEIR OWN TEST IN THEIR OWN LOCAL CONDITIONS TO CONFIRM THE SUITABILITY OF OUR PRODUCT FOR PARTICULAR USE. TECHNICAL SPECIFICATIONS ARE SUBJECT TO CHANGE.